

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

Claim 1. (currently amended): A low specific gravity unsaturated polyester resin composition for lamp reflectors, characterized in that the ~~compositions comprise~~ composition comprises from 40 to 210 parts by weight of an inorganic filler having an average particle size of at least 0.5 μm of and from 30 to 160 parts by weight of a hollow filler having a pressure resistance of at least $2,100 \times 10^4 \text{ N/m}^2$ based on 100 parts by weight of an unsaturated polyester resin and a crosslinking agent wherein the addition ratio by weight of the inorganic filler to the hollow filler lies within a range of 2:8 to 8:2.

Claim 2. (currently amended): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that the ~~compositions comprise~~ composition comprises from 35 to 75 parts by weight of the crosslinking agent based on 100 parts by weight of the unsaturated polyester resin and the crosslinking agent, said crosslinking agent ~~comprised of~~ comprising:

(A) diallylphthalate monomer or diallylphthalate prepolymer-(A), and

(B) a crosslinking agent other than said diallylphthalate monomer or said diallylphthalate prepolymer-(B); and

wherein the ratio by weight of the (A) to (B) lies in a range of 5:95 to 25:75.

Claim 3. (previously presented): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that said polyester resin is obtained by polycondensing a total of 100 moles consisting of 20 to 50 moles of propylene glycol, 25 to 65 moles of neopentyl glycol and 15 to 25 moles of bisphenol A or hydrogenated bisphenol A based on 100 moles of at least one unsaturated polybasic acid selected from a group formed from fumaric acid and maleic anhydride.

Claim 4. (previously presented): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that the inorganic filler has an average particle size of 15 μ m or less.

Claim 5. (previously presented): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that the hollow filler has a true specific gravity of 0.3 to 0.7.

Claim 6. (currently amended): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that molded articles of the resin ~~compositions~~ composition have a molding shrinkage ratio of -0.15 to +0.05%, a coefficient of linear expansion of $1.0 \times 10^{-5}/K$ to $2.5 \times 10^{-5}/K$, Barcol hardness of 5 to 25 when heated at 180°C and a specific gravity of 1.00 to 1.60.

Claim 7. (currently amended): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that the molded articles of the resin ~~compositions~~composition have a leveling of 5 to 20.

Claim 8. (currently amended): A molded article obtained by molding the low specific gravity unsaturated polyester resin ~~compositions~~composition for lamp reflectors according to Claim 1.

Claim 9. (original): A molded article according to Claim 8, characterized in that the molded article has a molding shrinkage ratio of -0.15 to +0.05%, a coefficient of linear expansion of $1.0 \times 10^{-5}/K$ to $2.5 \times 10^{-5}/K$, Barcol hardness of 5 to 25 when heated at 180°C and a specific gravity of 1.00 to 1.60.